



安徽景成新材料有限公司

Anhui Kingcham New Materials Co., Ltd.

Interior Matting Agent M61

- **Main components** Wax and catalyst
- **Technical parameters** Appearance: Light yellow powder
Bulk density: 550~650g/L .

- **Product characteristics**

The gloss of the coating film is above 30° gloss, non-reactive type, does not affect the weather resistance of the coating film, the surface is smooth, delicate and plump, and the dark coating film is large. The added surface will have a "waxy feel".

- **Usage**

Inner extrusion, adding 1~4.5%

- **Recommended formula**

Material	1	2	3	4
Excalibur SJ4ET	570			
DSMP4600		570		
DynaSky NH3307			570	
Guanghua GH2208				570
TGIC	42	42	42	42
KC701B	10	10	10	10
KC758	10	10	10	10
Benzoin	3	3	3	3
Matt barium	327	327	327	327
Carbon black	8	8	8	8
M-61	30	30	30	30
Total	1000	1000	1000	1000
Extrusion conditions	I ☑ 95°C, II ☑ 120°C			
Curing conditions	200°C*12min/190°C*15min			
Gloss%@60°	33	32	30	32

- **Formula description**

The content of matting filler increases, which is beneficial to matting.

- **Package and store**

Polyethylene lined kraft paper bags, each bag weighs 25kg net, and keep them sealed. Please store them in a cool and dry place, away from heat sources and avoid direct sunlight. The reasonable storage shelf life is 12 months.